



## Product Data Sheet

# Titanvene™ HM5250GA

## Large Blow Moulding Container Applications

Titanvene™ HM5250GA is a high molecular weight polyethylene grade supplied in pellet form for use in medium-large blow moulding applications. Titanvene™ HM5250GA is characterised by high environmental stress crack resistance, high impact strength, good rigidity and easy handling pellet form.

### Applications

- Intermediate bulk containers.
- Open top drum.
- Agricultural containers

### Recommended Processing Conditions <sup>(1)</sup>

Titanvene™ HM5250GA can be easily processed on normal polyethylene blow moulding machines at temperatures in the range of 200°C to 230°C.

### Food Contact Compliance

Titanvene™ HM5250GA can be used in food contact applications. Please contact your nearest PT. TITAN Petrokimia Nusantara representative for more detail of food contact compliance statements for the specific grade.

General Properties	Value <sup>(2)</sup>	Unit	Test Method
Melt Flow Rate (190°C/21.6 kg)	4.5	g/10 min	ISO 1133 Condition 7
Nominal Density	949	kg/m <sup>3</sup>	ISO 1183 Method D
Vicat Softening Point	127	°C	ISO 306
Melting Point	132	°C	ISO 3146 Method C

Mechanical Properties <sup>(3)</sup>	Value <sup>(2)</sup>	Unit	Test Method
Tensile Strength at Yield	25	MPa	ISO/R 527 Type 2 Speed C
Elongation at Break	1100	%	ISO/R 527 Type 2 Speed C
Charpy Impact Strength	25	kJ/m <sup>2</sup>	ISO 179 Type 1 Notch A
Flexural Modulus	1400	MPa	ISO 178
Hardness (Shore D)	65		ISO 868 Type D
Brittleness Temperature	-75	°C	ASTM D746
ESCR Condition B, F50 (4)	>1000	F50, hours	ASTM 1693

(1) The optimum processing conditions can be different from one machine to the others, depend on the mould and part design.  
(2) The values shown are typical values obtained by averaging a number of tests. Small divergences from the quoted figures may occur.  
(3) Measured on compression molded plaques.  
(4) Environment Stress Cracking Resistance 10% Igepal : CO-630

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.