



## Product Data Sheet

# Titanvene™ HD3840UA

## Rotational Moulding Applications

Titanvene™ HD3840UA is a medium density polyethylene, which has been specially developed for manufacturing large containers. Titanvene™ HD3840UA offers excellent UV light protection for outdoor exposure with high levels of UV light radiation where the use of inorganic pigments or carbon black is normally recommended.

### Applications

Titanvene™ HD3840UA is designed for large rotational moulding containers, traffic cone and garbage bin.

### Recommended Processing Conditions <sup>(1)</sup>

Titanvene™ HD3840UA can be easily processed on normal polyethylene rotational moulding machines at temperatures in the range of 180°C to 230°C.

### Food Contact Compliance

Titanvene™ HD3840UA can be used in food contact applications. Please contact your nearest PT. TITAN Petrokimia Nusantara representative for more detail of food contact compliance statements for the specific grade.

General Properties	Value <sup>(2)</sup>	Unit	Test Method
Melt Flow Rate (190°C/2.16 kg)	4	g/10 min	ISO 1133 Condition 4
Nominal Density	938	kg/m <sup>3</sup>	ISO 1183 Method D
Vicat Softening Point	117	°C	ISO 306
Melting Point	125	°C	ISO 3146 Method C

  

Mechanical Properties <sup>(3)</sup>	Value <sup>(2)</sup>	Unit	Test Method
Tensile Strength at Yield	17	MPa	ISO/R 527 Type 2 Speed C
Elongation at Break	1600	%	ISO/R 527 Type 2 Speed C
Charpy Impact Strength	12	kJ/m <sup>2</sup>	ISO 179 Type 1 Notch A
Flexural Modulus	650	MPa	ISO 178
Hardness (Shore D)	62		ISO 868 Type D

(1) The optimum processing conditions can be different from one machine to the others, depend on the mould and part design.  
(2) The values shown are typical values obtained by averaging a number of tests. Small divergences from the quoted figures may occur.  
(3) Measured on compression molded plaques.

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.