



Product Data Sheet

Titanvene™ HD5609AA

Tape and Monofilament Applications

Titanvene™ HD5609AA is a high density polyethylene suitable for extrusion and stretching process for filaments and tapes. Titanvene™ HD5609AA is characterised by its low gel content, stretching with few breaks and high tenacity.

Applications

Titanvene™ HD5609AA is designed for:

- Ropes.
- Mosquito nets and fishing nets.
- Woven tapes.
- Tarpaulin covers.

Recommended Processing Conditions ⁽¹⁾

Titanvene™ HD5609AA can be easily processed on normal polyethylene monofilament machines at temperatures in the range of 220°C to 265°C.

Food Contact Compliance

Titanvene™ HD5609AA can be used in food contact applications. Please contact your nearest PT. TITAN Petrokimia Nusantara representative for more detail of food contact compliance statements for the specific grade.

General Properties	Value ⁽²⁾	Unit	Test Method
Melt Flow Rate (190°C/2.16 kg)	0.9	g/10 min	ISO 1133 Condition 4
Nominal Density	954	kg/m ³	ISO 1183 Method D
Vicat Softening Point	125	°C	ISO 306
Melting Point	131	°C	ISO 3146 Method C

Mechanical Properties ⁽³⁾	Value ⁽²⁾	Unit	Test Method
Tensile Strength at Yield	25	MPa	ISO/R 527 Type 2 Speed C
Elongation at Break	1400	%	ISO/R 527 Type 2 Speed C
Charpy Impact Strength	11	kJ/m ²	ISO 179 Type 1 Notch A
Flexural Modulus	1400	MPa	ISO 178
Hardness (Shore D)	67		ISO 868 Type D

(1) The optimum processing conditions can be different from one machine to the others, depend on the mould and part design.

(2) The values shown are typical values obtained by averaging a number of tests. Small divergences from the quoted figures may occur.

(3) Measured on compression molded plaques.

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.