



Product Data Sheet

Titanvene™ HD6070UA

General Injection Moulding Applications

Titanvene™ HD6070UA is a high density polyethylene copolymer with a narrow molecular weight distribution protected by a UV stabilizer for outdoor exposure. Titanvene™ HD6070UA is suitable for a wide range of injection moulding applications. Titanvene™ HD6070UA is characterised by its easy processing, high rigidity/good impact resistance and high warpage resistance.

Applications

Titanvene™ HD6070UA is designed for:

- Crates, pails and containers.
- Pallets, structural foam and seats.

Recommended Processing Conditions ⁽¹⁾

Titanvene™ HD6070UA can be easily processed on normal polyethylene injection moulding machines at temperatures in the range of 200°C to 240°C.

Food Contact Compliance

Titanvene™ HD6070UA can be used in food contact applications. Please contact your nearest PT. TITAN Petrokimia Nusantara representative for more detail of food contact compliance statements for the specific grade.

General Properties	Value ⁽²⁾	Unit	Test Method
Melt Flow Rate (190°C/2.16 kg)	7.6	g/10 min	ISO 1133 Condition 4
Nominal Density	958	kg/m ³	ISO 1183 Method D
Vicat Softening Point	127	°C	ISO 306
Melting Point	132	°C	ISO 3146 Method C

Mechanical Properties ⁽³⁾	Value ⁽²⁾	Unit	Test Method
Tensile Strength at Yield	27	MPa	ISO/R 527 Type 2 Speed C
Elongation at Break	1500	%	ISO/R 527 Type 2 Speed C
Charpy Impact Strength	6	kJ/m ²	ISO 179 Type 1 Notch A
Flexural Modulus	1500	MPa	ISO 178
Hardness (Shore D)	68		ISO 868 Type D

(1) The optimum processing conditions can be different from one machine to the others, depend on the mould and part design.

(2) The values shown are typical values obtained by averaging a number of tests. Small divergences from the quoted figures may occur.

(3) Measured on compression molded plaques.

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.